

HIGH INTENSITY GLOSS (FOR LIP POT CONTAINER)

INGREDIENTS	%W/W
Phase A:	
Indopol H-100 (Polybutene)	41.00
Clearlan 1650 (Lanolin)	25.70
Paraffin 143/148 (Paraffin)	5.50
Thixcin R (Trihydroxystearin)	3.00
CERAPHYL 50-S (Myristyl Lactate)	9.50
ESCALOL 507 (Octyl Dimethyl PABA)	2.00
Propylparaben	0.15
Antioxidant	0.05
Phase B:	
#6905 D & C Orange #5 Zr. Lake (D & C Orange No. 5 Zirconium Lake)	0.75
CERAPHYL 847 (Octyldodecyl Stearoyl Stearate)	1.75
Phase C:	
FD & C Blue #1 Aluminum Lake in Castor Oil	0.30
Phase D:	
LUSTRA-PEARL GLIMMER (Mica (and) Titanium Dioxide)	10.00
Phase E:	
Fragrance	0.30

Procedure:

Prepare Phase B using two passes over a three roll mill at room temperature. Combine Phase A and heat to 85C until melted clear and homogeneous. Cool to 75C. add Phase B, Phase C and Phase D to it and mix thoroughly after each addition. Cool to just above congealing point - add Phase E and mix for 5 minutes and package.

Formulation #P107-31

PEARLY LIP GLOSS (FOR POT CONTAINER)

INGREDIENTS	% W/W
Phase A:	
Indopol H-100 (Polybutene)	41.00
Clearlan 1650 (Lanolin)	25.50
Paraffin 143/148 (Paraffin)	5.50
Thixcin R (Trihydroxystearin)	3.00
CERAPHYL 50-S (Myristyl Lactate)	12.50
ESCALOL 507 (Octyl Dimethyl PABA)	2.00
Propylparaben	0.15
Antioxidant	0.05
Phase B:	
SPECTRA-PEARL MTW (Mica (and) Titanium Dioxide (and) Carmine)	10.00
Phase C:	
Fragrance	0.30
Formulation #P107-29-1	

SOURCE: Van Dyk & Co., Inc.: Make Up Formulary: Formulations